# MicroC Foam® Polyurethane Foams

### PZ very soft series

Very soft Polyurethane Foams with super compression set resistance.


#### Benefits

- Dust, liquid, light and sound sealing
- Long term spring force
- Super compression set resistance
- Resistant to moisture

#### **Applications**

- LCD and speaker gasket
- Camera lens seals
- Connector cushion pad
- Battery pad

## **Naming**




#### Storage

Store in a dry and cool place

No direct exposed to UV or solvent

Properties	Test Method	PZ Series					
Density, kg/m³ Tolerance,%	ASTM D3574 Test A	145 ±10	200 ±10	240 ±10	320 ±10	400 ±10	480 ±10
Thickness,mm Tolerance,%		0.3~2.0 ±10	0.5~4.0 ±10	0.5~5.0 ±10	2.0 ±10	0.4~3.0 ±10	0.3~0.5 ±10
Compression Set % max, 50%, 70°C	ASTM D3574 Test D	10					
Compression Force Deflection, Range kPa	25% deflection	1.7~9.2 5	2~17 9	2~24 12	7~35 20	8~58 32	16~94 54
Color		Black					
Recommended Constant Use, max		70°C					
Recommended Intermittent Use, max		120°C					
Embrittlement	ASTM D746	-20°C -18°C -12°C -10°C				-10°C	
Cold Flexibility	MIL-P-12420D -40°C	Pass					



MicroC Foam® is a registered trademark of Shengying Corporation.

Shengying new material technology (Changzhou) Co., LTD

Suzhou Sales office

Rm816, Zhiyuan International Business Building, #101, Kefa Road, Science and Technology Tower, Hi-Tech Zone, Suzhou. Tel: 0512-66890180 Fax:0512-66890196